Research and Application Status of Envelope Structures for Fabricated Substations in China

Xueqing Sheng^{1.,}, Shengjun Pan^{1.,,}, Jiahui Chen^{1.,,,}

¹Hangzhou Electric Power Design Institute Co.,Ltd.Hangzhou 132012,China;

Abstract—In recent years, Chinese prefabricated buildings have re-heated and showed rapid growth. This paper analyzes the performance of the existing assembled wall panels in the Chinese market by comparing the performance of different materials and optimizing the selection of the envelope structure of the assembled substation. Studies have shown that the use of prefabricated building systems can achieve the goal of shortening the construction period, reducing manual labor, no waste during construction, and no wet work on site.

1 Introduction

Since 2014, China has successively issued a number of important policy documents to promote the development of prefabricated buildings. The State Council issues the "Opinions on Promoting the Sustainable and Healthy Development of the Construction Industry" which requires by 2025, the proportion of prefabricated buildings in new buildings will reach 30%. At the same time, prefabricated buildings have been widely used in industrial plants.

2 Characteristics of the envelope structure of traditional substations

The substation envelope structure generally adopts the on-site masonry construction method, and the material selection is mostly brick masonry. During the construction process, on-site procurement of sand and stone brick reinforced cement and other building materials was used. This kind of operation has uneven engineering quality due to the uneven technical level of the construction teams. At the same time, long period of construction which makes the on-site civilized management more difficult is common quality problem in traditional envelope structures. Moreover, the traditional surface decoration is generally sand rubbing or ordinary plastering, or a decorative coating layer, which will cause some common quality problems. For example, ordinary brick wall plastering is prone to plastering hollows, cracks, surface cracks, shedding, anti-alkali, fluff, etc. These common problems are difficult to overcome due to the difference in the quality of the floor materials used.

3 Substation assembled wall

3.1 Common assembled wall structure

In developed countries in Europe and the United States, due to higher labor cost, the construction of substations is less likely to use cast-in-situ concrete structures, but more steel structures and finished envelope structures (such as profiled steel plates) are used. The main structure of indoor substations in Japan generally uses clear water concrete technology, and the inner partition walls are assembled with finished wall panels produced by the factory.

Since the Economic Reform and Open Up in China, with the economic development, prefabricated buildings have been widely used in industrial plants. The light assembled substation actively explored by the National Electric Power Company is an important innovation that deeply implements the requirements of the State Grid Corporation's "two-type, one-ization" construction. And the prefabricated wall is a key link in implementing this policy.

3.2 B. R & D significance of prefabricated wall panels

With the economic development of the society, the scale of substation construction has gradually increased. The prefabricated wall panel can effectively shorten the construction period from the manufacturer's prefabrication to the crane site installation, and its construction period can be 40% ahead of time, which is conducive to site safe and civilized construction management. The internal quality and performance quality of the installation have met the requirements of

^{*:}sxq_ks@163.com; **:496183759@qq.com;***:gyyomi@163.com

https://doi.org/10.1051/e3sconf/202018903037

the acceptance specification of the substation, avoiding the common quality problems of cracking or peeling of the brick wall plastering layer in the past. Production, standard and simplified prefabricated substation is one of the long-term development directions of substation construction.

3.3 Advantages of prefabricated wallboard

(1) Industrialized production: The project department proposes a production plan. And then according to the quality requirements of the project department and the schedule of the substation, the manufacturer products, processes and delivers prefabricated wallboard to the construction site.

(2) Easy and quick installation: Easy and quick installation of prefabricated wallboard effectively shortens the construction period, fully realizes the mechanized construction, reduces the workload of wet work on site and promotes the phenomenon of safe and civilized construction on site.

(3) Stable structural performance: Prefabricated wallboard adopts reinforced concrete column and slab structure, and its structural strength and anti-overturning performance are much larger than brick wall panels.

(4) Green environmental protection. Neat and beautiful appearance.

4 Application status of prefabricated wallboard

There are five main prefabricated wall boards: Auto lightweight concrete, glass fiber reinforced cement board, metal rock wool sandwich board, fiber reinforced cement board, and acrylic nitrile-styrene board.

4.1 Auto lightweight concrete (ALC board)

ALC board uses silica sand, cement, lime, etc. as the main raw materials and it is a new type of green environmental protection building material with good performance. It can be used as the internal and external wall envelope structure and roof board in industrial and civil buildings.

4.2 Glass-fiber reinforced cement (GRC board)

Glass-fiber reinforced cement is a new type of composite material, which is composed of cement, alkali-resistant glass fiber and water as main raw materials. Adding glass fiber to cement mortar can greatly improve its bending strength, tensile strength and impact strength. In addition, due to the flexibility of glass fiber and various methods of use, it has given glass fiber reinforced cement composites good process performance, making it more suitable for making various thin-walled products with complex shapes. The common used GRC products mainly include GRC lightweight hollow partition boards and GRC composite exterior wall boards.

4.3 Metal Rock Wool Sandwich Board (LCF board)

The metal rock wool sandwich panel is made by bonding two laminated steel plates and the intermediate structure rock wool together with a special adhesive and then curing by pressure. The top and bottom or inside and outside panels of the rock wool sandwich boards are coated steel sheets, and the profiled steel sheets are formed by rolling and cold bending. The core layer is a non-combustible, hard, hydrophobic rock wool board or mineral wool board. Adhesive is used for bonding, and the fiber direction of the core layer is perpendicular to the panel. After the forming of the sandwich panel, the upper and lower floors of steel plates are integrated with rock wool and they work together. Therefore, it is a new type of multifunctional composite board.

It is widely applicable to a variety of large-scale industrial plants, roofing and wall envelope materials of public buildings, especially the outer envelope materials of commercial buildings and civil buildings that require high building facades.

4.4 Fiber reinforced cement board (FC board)

FC board is formed of wood pulp fiber, cement, sand, additives, water and other organic and inorganic substances after mixing, molding, pressing, high-temperature autoclaving and surface treatment. It is a type of lightweight board without asbestos and other harmful substances. And it can be molded into a variety of thicknesses and densities.

FC board inherits the advantages of waterproofing and anti corrosive of cement products, and overcomes the disadvantages of easy drying and shrinkage of cement products. It also increased strength. Therefore, FC board is a stable, environmentally friendly and high-strength material.

4.5 Acrylonitrile-styrene board (AS board)

AS prefabricated wallboard is an integral part of prefabricated building system. This complete system is the research results of Waseda University, Japan and has more than 60 years of development and practice. It is divided into external wall system and interior finished wall system. The whole system includes wall materials, functional materials, link materials and closed materials.

AS board belongs to silicate concrete products. The main materials are cement, silica, polyester fiber, pulp fiber, and additives.

Here are the figures of ALC board, GRC board, LCF board, FC board, AS board from Figure 1 to Figure 6.





Figure 4: LCF board



Figure 2: GRC lightweight hollow



Figure 5: FC board



Figure 3: GRC composite exterior wallboard



Figure 6: AS board

Material performance comparison 5

Here is the comparison of mechanical and physical properties. As is shown in Table 1.

Table 1: Comparison of mechanical and physical pro	perties
--	---------

	Table 1. Comparison of meenamear and physical properties
SPECIES	MECHANICAL AND PHYSICAL PROPERTIES
ALC board	Lightweight and high-strength, with good durability, sound insulation and sound absorption, slightly abrasion resistance
GRC board	Light weight, high strength, high toughness, high weather resistance, poor water resistance
LCF board	High shear strength and certain toughness, the strength is not good enough, and the waterproof performance is poor
FC board	
AS board	Lightweight and high strength, good environmental protection, good waterproof and moistureproof performance
	Has a strong ability to withstand loads, resistance to chemical reactions, thermal deformation resistance and geometric stability, high durability, and strong resistance to freeze-thaw

The following are the specific values of the physical properties of the five types of boards, and they are shown from Table 2 to Table 6.

Table 2: Various physical properties of ALC board

Physical properties	Value	
Mass per unit volume(kg/m)	650	
Compressive strength(N/mm ²)	>3	
Bending strength(N/mm ²)	0.78-1.18	
Shear strength(N/mm ²)	0.39-0.88	
Tensile Strength(N/mm ²)	0.39-0.59	

Table 3: Various physica	ll properties of GRC board	
Physical properties	Value	
Flexural strength(Mpa)	>18	
Compressive strength(Mpa)	>40	

		Table 4: Various physical proper	
	Physical properties Tensile strength(kgf/m ²)		Value
			average value>0.1
	Compressive strength(kgf/m ²)		1.5
		Table 5: Various physical prope	rties of FC board
	Physical	properties	Value
	Flexural stre	ength(kg/cm ²)	≤300
	Anti-fold st	rength(Mpa)	15-20
		Table 6: Various physical prope	rties of AS board
	Physical	properties	Value
Proportion(g/cm ³)		on(g/cm ³)	1.05
Compressive strength(Mpa)		strength(Mpa)	14
		the comparison of fire perf	ormance and the comparison of econom ormance.
	~ .	Table 7: Comparison of thermal inst	
	Species	Insulation performance	Heat transfer coefficient(W/m ² ·k)
A	LC board	10 times than the thermal insulation properties of ordinary concrete	0.75(200mm board thickness)
G	RC board	Good thermal insulation performance Good thermal insulation performance	e 0.588(200mm board thickness)
L	CF board	Good thermal insulation performance and good thermal insulation	wall)
F	FC board	performance	0.596(215mm thick wall)
A	AS board	General thermal insulation performance	2.22

Species	Fire performance	Fire resistance(h)
ALC board	Non-combustible, high fire resistance	e 3.2(100 mm thick ALC board)
	Come with fire insulation	
GRC board	LCF core material is	2
LCF board	non-combustible material	Z
	Good fire resistance,	Fire resistance in line with national
FC board	non-combustible	standards
		4.5(100 mm thick AS fabricated wall
AS board Good fire performance	panels)	
ring the perfo	ormance of the above five subs	titute for traditional building envelope

Comparing the performance of the above five wallboard materials, it can be seen that the AS boards have better performance in all aspects, and its fire resistance is better than ALC boards under the same conditions. ALC boards have better performance in all aspects , but poor wear resistance. Compared with AS assembled wall boards, ALC boards are more of a

substitute for traditional building envelopes. The disadvantages are low strength and non-decorative nature, and secondary decoration of external surfaces is required. After the completion of the prefabricated building, the interior appearance is not much different from that of a conventional building.

Species	$Price(\frac{1}{2}/m^2)$	Installation and maintenance
ALC board	<700	Cheap price with high maintenance cost
GRC board	700~800	Moderate price with some maintenanc costs
LCF board	1400~1600	Expensive with low maintenance cost
FC board	1000~1100	Moderate price with some maintenanc costs
	1000~1200	Higher prices and lower maintenance

AS board

costs

Note: The prices in the table are comprehensive prices, including internal support such as keel and labor costs.

Comparing the economic performance of the above five types of wallboard materials, it can be seen that the price of LCF boards is more expensive, so LCF boards are not a economical enough choice. AS boards, ALC boards and GRC boards are lower in price, and they are more suitable for industrial buildings such as substations that do not require particularly high facades. The ALC boards, FC boards, and GRC boards do not have a decorative surface. They need to be re-decorated on the spot. So there are certain maintenance costs later.

6 Conclusion

With the economic development of society, the envelope structure of prefabricated buildings becomes more and more important in the substation construction. This structure makes a full consideration of the material performance and economic indicators. And it can effectively shorten the construction period, reduce costs, and implement the new concept of green building.

Acknowledgments

The authors gratefully thank Zhejiang Electric Power Corporation for providing the technical support. This work was supported by Research and Application of Key Technologies for Modular Construction of Fabricated Substation(SGTYHT/18-JS-202).

Reference

- Kazem H, Bunn W G, Seliem H M, et al. Durability and Long Term Behavior of FRP/Foam Shear Transfer Mechanism for Concrete Sandwich Panels[J]. Construction and Building Materials, 2015, 98:722-734.
- JCI.Method of Test for Flexural Strength and Flexural Toughness of Fiber Reinforced Concrete:JSCE-SF 4[S]. Tokyo:Japan Concrete Institute, 1984.
- 3. Felicetti R, Gambarova P G, Bamonte P. Thermal and Mechanical Properties of Light-Weight Concrete Exposed to High Temperature[J]. Fire and Materials, 2013, 37(3):200-216.
- Ng S C, Low K S, Tioh N H. Thermal Inertia of Newspaper Sandwiched Aerated Lightweight Concrete Wall Panels: Experimental Study[J]. Energy and Building, 2011, 43(10):2956-2960.
- Oka H, Yamada S, Lgarashi S, et al. Stiffness and Strength of ALC Core Sandwich Slabs Adhesively Bonded with Steel Skins[J]. Journal of Structural and Construction Engineering, 2011, 76(2): 427-435.